

# Product Data

## HEMPEL'S RUBBING LIQUID 69021



<b>Description:</b>	HEMPEL'S RUBBING LIQUID 69021 is a fine abrasive rubbing compound.
<b>Recommended use:</b>	Restores and renews the gloss and colour to gelcoat and painted surfaces.  For removal of light scratches, stains, oxidation and other irregularities from most surfaces, including aluminium.  Can be used for both manual and machine polishing.
<b>Availability:</b>	Part of European Yacht assortment. Local availability subject to confirmation.
<b>PHYSICAL CONSTANTS:</b>	
Shade nos/Colours:	99980/ Off-white.
Flash point:	80 °C [176 °F]
Specific gravity:	1.4 kg/litre [11.3 lbs/US gallon]
pH:	7
VOC content:	362 g/l [3 lbs/US gallon] <i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
<b>APPLICATION DETAILS:</b>	
<b>Safety:</b>	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.
<b>SURFACE PREPARATION:</b>	Clean and degrease the surface with HEMPEL'S PRE-CLEAN 67062 or HEMPEL'S BOAT SHAMPOO 67284 to remove dirt and other contaminants, rinse with fresh water. Allow the surface to dry.
<b>PRODUCT APPLICATION:</b>	<b>By hand:</b> Shake well before use. Spread HEMPEL'S RUBBING LIQUID 69021 uniformly on to the surface, rub with circular movements until almost dry. Wipe off with a clean cloth. Apply more HEMPEL'S RUBBING LIQUID 69021 until the required finish has been obtained. <b>By rotating polishing machine</b> (The most efficient method for large areas): Spread HEMPEL'S RUBBING LIQUID 69021 uniformly on to the surface and polish with the polishing machine. Work on small areas to avoid the compound drying. Dry compound may burn gelcoat. Use only clean compound pads as dirty or contaminated pads can cause scratches and swirl marks. Clean the compound pad regularly while in use. Keep the compound wet, adding some droplets of water onto the compound and the surface can help this process. Keep compound pad flat or at a minimum angle, the use of the edge of the pad may cause burning or swirl marks. Recommended use with a polishing machine rated at 1500-2500 RPM.  Painted surfaces should dry for at least 30 days before using the product.
<b>APPLICATION CONDITIONS :</b>	Do not expose to frost. Do not apply in direct sunlight. Minimum surface temperature: 5°C/41°F.
<b>SUBSEQUENT COAT:</b>	If high gloss is desired, apply: HEMPEL'S CUSTOM MARINE POLISH 67444. Finish with: HEMPEL'S WAX 69033 or HEMPEL'S WAX TecCel 69034
<b>REMARKS:</b>	Silicone and ammonia free.
<b>Note:</b>	<b>HEMPEL'S RUBBING LIQUID 69021</b>
<b>ISSUED BY:</b>	HEMPEL A/S <span style="float: right;">6902199980</span>

This Product Data Sheet supersedes those previously issued.  
For explanations, definitions and scope, see "Explanatory Notes" available on [www.hempel.com](http://www.hempel.com). Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.  
The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.